

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Die	Doped silicon	Silicon (Si)	7440-21-3	0.33836	100.0	0.77
			Subtotal	0.33836	100	0.77
Post-plating	Tin solder	Bismuth (Bi)	7440-69-9	0	0.0	0
	Tin solder	Tin (Sn)	7440-31-5	1.61692	99.99	3.67963
	Tin solder	Copper (Cu)	7440-50-8	0	0.0	0
	Tin solder	Lead (Pb)	7439-92-1	0.00016	0.01	0.00037
	Tin solder	Antimony (Sb)	7440-36-0	0	0.0	0
			Subtotal	1.61708	100	3.68
Lead Frame	Copper alloy	Misc. Phosphor compounds (generic)	7723-14-0	0.00789	0.02	0.01794
	Copper alloy	Iron (Fe)	7439-89-6	0.03154	0.08	0.07178
	Copper alloy	Copper (Cu)	7440-50-8	39.30696	99.7	89.45084
	Pure metal layer	Silver (Ag)	7440-22-4	0.07885	0.2	0.17944
			Subtotal	39.42524	100	89.72
Adhesive	Polymer	Paraffin wax	8002-74-2	0.21971	20.0	0.5
	Polymer	Epoxy resin system		0.08789	8.0	0.2
	Filler	Silver (Ag)	7440-22-4	0.79097	72.0	1.8
			Subtotal	1.09857	100	2.5
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	1.43769	2.5	3.27175
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.31307	7.5	9.81525
	Filler	Silica -amorphous-	7631-86-9	21.2778	37.0	48.4219
	Pigment	Carbon black	1333-86-4	0.28754	0.5	0.65435
	Polymer	Epoxy resin system		8.62614	15.0	19.6305
	Filler	Silicon Dioxide (SiO2)	14808-60-7	21.2778	37.0	48.4219
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	0.28754	0.5	0.65435
			Subtotal	57.50758	100	130.87
Wire	Pure metal	Copper (Cu)	7440-50-8	0.01318	100.0	0.03
			Subtotal	0.01318	100	0.03
			Total	100.00001	100	227.57

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.