

External_Type	Material_Group	Substances	CAS_Number	Mass	Mass_Percentage_in_Leaf	Massmg
Die		Silicon (Si)	7440-21-3	0.16287	100.0	3.403
			Subtotal	0.16287	100	3.403
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.01284	100.0	0.26839
			Subtotal	0.01284	100	0.26839
Solder Wire	Tin alloy	Tin (Sn)	7440-31-5	0.01291	10.0	0.26973
	Silver alloy	Silver (Ag)	7440-22-4	0.00258	2.0	0.05395
	Lead alloy	Lead (Pb)	7439-92-1	0.1136	88.0	2.37362
			Subtotal	0.12909	100	2.6973
Wire	Pure metal	Aluminium (Al)	7429-90-5	0.1007	100.0	2.10415
			Subtotal	0.1007	100	2.10415
Lead Frame	Copper alloy	Phosphorous (P)	7723-14-0	0.00703	0.03	0.14694
	Pure metal layer	Zinc (Zn)	7440-66-6	0.00469	0.02	0.09796
	Pure metal layer	Tin (Sn)	7440-31-5	0.00703	0.03	0.14694
	Pure metal layer	Iron (Fe)	7439-89-6	0.02579	0.11	0.53877
	Pure metal layer	Copper (Cu)	7440-50-8	23.39678	99.81	488.8594
			Subtotal	23.44132	100	489.79001
Post-plating	Pure metal	Tin (Sn)	7440-31-5	0.24729	100.0	5.167
			Subtotal	0.24729	100	5.167
Mould Compound	Polymer	Tetrabromobisphenol A/Epichlorohydrin polymer	40039-93-8	2.27718	3.0	47.58
	Polymer	Phenol Formaldehyde resin (generic)	9003-35-4	4.55435	6.0	95.16
	Polymer	Epichlorohydrin/o-Cresol/Formaldehyde polymer (generic)	29690-82-2	7.59059	10.0	158.6
	Carbon Black	Carbon black	1333-86-4	0.37953	0.5	7.93
	Filler	Misc. Silica compounds (generic)	14808-60-7	59.20658	78.0	1237.08
	Flame retardant	Antimony Trioxide (Sb2O3) - cas no. 1309-64-4	1309-64-4	1.89765	2.5	39.65
			Subtotal	75.90588	100	1586
			Total	99.99999	100	2089.42985

Disclaimer

All information in this document is furnished for exploratory or indicative purposes only. All information in this document is believed to be accurate and reliable. However, WeEn Semiconductors does not give any representations or warranties as to the accuracy or completeness of such information and shall have no liability for the consequences of use of such information. WeEn Semiconductors may make changes to information published in this document at any time and without notice. Minor deviations may occur in the products from different manufacturing location. This document supersedes and replaces all information supplied prior to the publication hereof. Nothing in this document may be interpreted or construed as an offer to sell products that is open for acceptance or the grant, conveyance or implication of any license under any copyrights, patents or other industrial or intellectual property rights.